

DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 26, 2021

Mr. Eddy Jones
MEDIA ONE DIGITAL IMAGING SOLUTIONS, LLC
11752 Markon Drive
Garden Grove, CA 92841

Reference: Laboratory Test Report Lab
Identification No. 47655
Invoice No. 78659

Dear Mr. Jones:

One (1) fabric sample, identified as **TXCJBB**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	3.41
2	0.0	13.02
3	0.0	1.98
4	0.0	6.65
5	0.0	8.85
6	0.0	14.45
7	0.0	14.04
8	0.0	11.28
9	0.0	17.12
<u>10</u>	<u>0.0</u>	<u>12.76</u>
AVG	0.0	10.36

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.


If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr





DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

October 18, 2022

Mr. Todd Braithwaite
MEDIA ONE DIGITAL IMAGING SOLUTIONS, LLC
11752 Markon Drive
Garden Grove, CA 92841

Reference: Laboratory Test Report
Lab Identification No. 52318
Invoice No. 83595

Dear Mr. Braithwaite:

One (1) sample, identified as **TXNL**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Test Results</u>		
<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	15.56
2	0.0	11.06
3	0.0	13.63
4	0.0	8.28
5	0.0	19.71
6	0.0	13.75
7	0.0	15.64
8	0.0	16.71
9	0.0	14.19
<u>10</u>	<u>0.0</u>	<u>17.73</u>
AVG	0.0	14.63

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

Sincerely,

Brian S. Dement

BSD/mr

